



Confidential Report

Our Ref: 26/02804E/12/20



1066

**Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339**



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 18 December 2020

Our Ref: 26/02804E/12/20

Your Ref: ---

Page: 1 of 4

Client:

Polyflor Limited

Radcliffe New Road
Whitefield
Manchester
M45 7NR

Job Title:

Fire Test on One Sample of Flooring

Clients Order Ref:

2252040

Date of Receipt:

14 December 2020

Description of Sample:

One sample of flooring, referenced;.
Product Name: Polyflor Wood fx PUR
Nominal Thickness: 2.0mm
Weight Per Unit Area: 2.78kg/m²
Batch Number: AA255
Shade: 4045 Jetstone

Work Requested:

We were asked to make the following test(s):

AS ISO 9239-1

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the samples submitted and as described in the report.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 18 December 2020

Our Ref: 26/02804E/12/20
Your Ref: ---

Page: 2 of 4

Client: Polyflor Limited

FIRE TESTS ACCORDING TO AS ISO 9239-1:2003

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2002)

Date of Test: 18/12/2020

Conditioning

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of (6 ± 1) mm and a density of $(1,800 \pm 200)$ Kg/m³ representing the standard substrate of Class A1fl or A2fl.

Mounting Method

The specimens of floor covering were tested adhered to a 6mm fibre cement board, as defined in BS EN 13238:2010, using Uzin KE66 adhesive.

Procedure

The test was carried out in accordance with AS ISO 9239-1:2003. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m² to 1.0 kW/m² along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, whichever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.

Date: 18 December 2020

Our Ref: 26/02804E/12/20
Your Ref: ---

Page: 3 of 4

Client: **Polyflor Limited**

Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.

Specimen No.	Direction of spec.	Smoke Obscuration/ Development		Maximum Flame front (mm)	Heat Flux-30 (HF-30) (kW/m ²)	Critical Heat/Radiant Flux (CHF/CRF) (kW/m ²)	Duration of Flaming (sec)
		Max %	% x min				
1	Machine	91	186	115	10.6	10.6	750
2	Across	100	265	155	9.9	9.9	740
3	Across	98	255	152	10.0	10.0	730
4	Across	100	247	165	9.7	9.7	731
Mean of 3 specs.	Across	99	256	157	9.9	9.9	734

Distance Burnt (mm)	Time for each specimen to burn (s)			
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
50	145	160	180	185
100	210	215	240	220
150	---	250	315	260

Note

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk


Date: 18 December 2020


Our Ref: 26/02804E/12/20

Your Ref: ---

Page: 4 of 4

Client: Polyflor Limited

Reported by:  B Marsden (Mrs), Senior Fire Technician

Countersigned by:  P Doherty, Executive Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.